


General Feature

- Absorbent Glass Mat(AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.



SPECIFICATION









Nominal voltage	12V
Number of cell	6
Length(mm/inch)	520/20.5
Width(mm/inch)	268/10.6
Height(mm/inch)	220/8.66
Total Height(mm/inch)	224/8.82
Approx. Weight(kg/lbs)	69.5/153.2

Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

Performance Characteristics

Capacity 77°F(25°C)	20 hours rate(13A 10.8V)	260Ah
	10 hours rate(25A 10.8V)	250Ah
	5 hours rate(43A 10.5V)	213Ah
	1 hour rate(159A 9.6V)	159Ah
Internal Resistance	Full charged battery 77°F(25°C):4mΩ	
Capacity affected by Temperature (10 hour rate)	104°F(40°C)	102%
	77°F(25°C)	100%
	32°F(10°C)	85%
	5°F(-15°C)	65%
Self-Discharge 68°F(20°C)	Capacity after 3 month storage	90%
	Capacity after 6 month storage	80%
	Capacity after 12 month storage	60%
Max discharge current 77°F(25°C):1250A(5S)		
Charge (Constant Voltage)	Float:13.6 to 13.8V/77°F/(25°C)	
	Cycle:14.4 to 14.7V/77°F/(25°C)	
	Max Current:62.5A	



Discharge Constant Current (Amperes at 77°F 25°C)

End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V		577	401	265	159	69.0	44.5	25.5	13.3
1.65V		552	382	259	156	68.0	44.0	25.4	13.2
1.70V		527	363	251	153	67.0	43.5	25.3	13.2
1.75V		502	343	243	150	65.8	43.0	25.2	13.1
1.80V		473	318	234	145	64.3	42.3	25.0	13.0

(Note) The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum values.

Discharge Constant Power (watts at 77° F 25°C)

End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	3h	5h
1.60V		981	738	511	394	322	187	143	94.6
1.65V		966	733	508	392	320	186	142	94.3
1.70V		948	726	504	389	317	184	141	94.0
1.75V		913	718	501	387	314	183	140	93.7
1.80V		875	707	496	384	310	181	138	93.3

(Note) The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum values.